



BLACK COMMODITY is a high quality recycled resin sourced exclusively from rotomolding.

It helps reduce plastic waste with great mechanical properties and aesthetics.



Find More Information



www.rotopolymers.com + 1 216 591 0175 info@rotopolymers.com

BLACK COMMODITY

METHOD²

VALUE

DENSITY

D1505 Reference MA-01 Own Method

0.935 g/cm³

MELT INDEX @190°C/2.16 kg

ASTM D1238

5.0 g/10 min

TENSILE STRENGTH AT YIELD¹
@ 50mm/min

ASTM D638

1,770 psi (12.2 MPa)

LOW TEMPERATURE IMPACT

@ -40°C¹

ARM 1/8" specimen 47 ft/lb (63.5 J)

FLONGATION AT BREAK¹

ASTM D638

230 %







- ¹ Rotational Molded
- ² Test methods may be modified to accommodate conditions or laboratory limitations
- Test equipment upper limit for elongation is 600%

The following are typical properties and are not to be construed as specifications.

Tests were done on natural, unpigmented resin.

User is advised to make its own determination of this product's suitability for its intended use.

Roto Polymers makes no warranty expressed or implied regarding the suitability of this product in application.

www.rotopolymers.com
+ 1 216 591 0175
info@rotopolymers.com